

### Amendments to the Claims

Claims 1-6 (Cancelled).

Claim 7 (Previously presented):      An aluminum alloy coating process for cast iron and steel products, consisting of:  
preparing a surface of the product by jet-abrasion; and then  
plunging the prepared product into an aluminum melt having a temperature of 660 – 680°C and alloyed with zinc, silicon, magnesium and tin having mass percentages of:  
    zinc 7.0-10.0  
    silicon 3.0-5.0  
    magnesium 0.5-1.5  
    tin 0.2-0.5, and  
for 70-80 seconds so as to coat the product with the alloy without the use of flux.

Claim 8 (Cancelled).